

## **BITUMEN GRADE 110/10**

Property / Unit	Value	Test Method
Relative density / S.G .at 25°C ,g / ml	1.01-1.06	ASTM D-70
Penetration at @25°C ,0.1 mm	105-115	ASTM D 5
Softening point °C (Ring and Ball)	10-20	ASTM D-36
Flash point °C (Cleveland Open Cup)	200	ASTM D-92
Loss on Heating % wt by mass	0.2	ASTM D-6
Ductility at 25°C cm ,min		ASTM D113
Solubility in Toluene %wt min	99	EN12592:2000