

BITUMEN 90-15

Characteristic	Value	Test Method
Specific Gravity @ 25/25°C	1.05 approx	ASTM D-70
Penetration @ 25°C (dmm)	10-20	ASTM D-5
Softening Point (°C)	85-95	ASTM D-36
Ductility @ 25°C (cm)	1.5 min	ASTM D-113
Loss on Heating (%wt)	0.2 max	ASTM D-6
Flash Point (°C)	250 min	ASTM D-92
Solubility in CS₂ (%wt)	99 min	ASTM D-4