

### BITUMEN CSS-1h

Property	Min	Max	Test Method
Viscosity, Say bolt Furol at 25°C,SFS	20	100	ASTM D244
Storage stability Test, 24-h, %	-	1	ASTM D6930
Particle Charge Test	Positive		ASTM D244
Sieve Test, %	-	0.1	ASTM D6933
Cement Mixing Test,%	-	2.0	ASTM 6935
Distillation			
Residue %	59	-	ASTM D244
Test On Residue From Distillation			
Penetration, 25°C(77°F), 100g, 5s	40	90	ASTM D5
Ductility, 25°C(77°F), 5 cm/min, cm	40	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042