

**BITUMEN MC 30**

| Characteristic  | Value   | Test Method |
|---|---------|-------------|
| Kinematic Viscosity at 60°C (cSt)                       | 30-60   | ASTM D-2170 |
| Flash Point (top open cup) (°C)                         | 38 min  | ASTM D-3143 |
| Distillate, %volume of total distillate to at 360°C:    |         |             |
| To 225°C  | 25 max  | ASTM D-402  |
| To 260°C  | 40-70   |             |
| To 316°C  | 75-93   |             |
| Residue from Distillation to 360°C (%Vol by difference) | 50 min  |             |
| <b>Test on Residue from Distillation</b>                |         |             |
| Viscosity at 60°C                                       | 30-120  | ASTM D-2170 |
| Penetration at 25°C (dmm)                               | 120-250 | ASTM D-5    |
| Ductility at 25°C (cm)                                  | 100 min | ASTM D-113  |
| Solubility in Trichloroethylene (%wt)                   | 99 min  | ASTM D-2042 |



Water Content (%vol)

0.2 max

ASTM D-95

