

**BITUMEN MC 800**

| Characteristic  | Value    | Test Method |
|---|----------|-------------|
| Kinematic Viscosity@ 60°C (cSt)                         | 800-1600 | ASTM D-2170 |
| Flash Point (top open cup) (°C)                         | 66 min   | ASTM D-3143 |
| Water Content (%vol)                                    | 0.2 max  | ASTM D-95   |
| Distillate, %volume of total distillate to @ 360°C:     |          |             |
| to 225°C  | ---      | ASTM D-402  |
| to 260°C  | 0-35     |             |
| to 316°C  | 45-80    |             |
| Residue from Distillation to 360°C (%Vol by difference) | 75 min   | ASTM D-402  |
| <b>Test on Residue from Distillation</b>                |          |             |
| Penetration @ 25°C (dmm)                                | 120-250  | ASTM D-5    |
| Ductility @ 25°C (cm)                                   | 100 min  | ASTM D-113  |
| Solubility in Trichloroethylene (%wt)                   | 99 min   | ASTM D-2042 |