

BITUMEN K160

Property	Min	Max	Test Method
Viscosity, Say bolt Furol at 50°C,SFS	20	100	ASTM D244
Storage stability test, 24-h, %	-	1	ASTM D6930
Demulsibility, 35 ml, 8% Dioctyl sodium sulfosuccinate, %	40	-	ASTM D6936
Particle Charge Test	Positive		ASTM D244
Sieve Test, %	-	0.1	ASTM D6933
Distillation			
Solvents, By Volume Of Emulsion %	-	3	ASTM D6997
Residue %	60	-	ASTM D244
Test On Residue From Distillation			
Penetration, 25°C(77°F), 100g, 5s	100	250	ASTM D5
Ductility, 25°C(77°F), 5 cm/min, cm	40	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042