

BITUMEN K170

Property	Min	Max	Test Method
Viscosity, Say bolt Furol at 50°C,SFS	20	-	ASTM D7496
Storage stability test, 24-h, %	-	1	ASTM D6930
Particle charge test	positive		ASTM D244
Sieve test, %	-	0.1	ASTM D6933
Distillation:			
Oil distillate, by volume of emulsion, %	-	4	ASTM D6997
Residue, %	67	-	ASTM D6997
Test on residue from distillation :			
Penetration, 25°C (77°F), 100 g, 5 s	60	250	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	20	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTMD2042