

**Light & Heavy RPO (Rubber Process Oil)**

Characteristic	Test Method	Value	
		Heavy	Light
Kinematic Viscosity @ 100 °C (cSt)	ASTM D445	35 min	35 max
Density @ 15 °C	ASTM D1298	1.050	1.010
Flash Point (°C)	ASTM D93	200-230	200-230
RI @ 70 °C	ASTM D1218	1.56	1.55
Oil Type	----	Aromatic	