

**Light Slack Wax 3 To 8 % Oil Content**

<b>Characteristic</b>	<b>Test Method</b>	<b>Value</b>
<b>Kinematic Viscosity @ 100 °C</b>	<b>ASTM D445</b>	<b>3 – 6</b>
<b>Oil Content (%wt)</b>	<b>ASTM D721</b>	<b>3 – 8</b>
<b>Melting Point</b>	<b>ASTM D87</b>	<b>55 – 60</b>
<b>Color</b>	<b>ASTM D1500</b>	<b>0.5 - 3</b>