

RPO 145

Characteristic	Test Method	Result
Kinematic Viscosity @ 40 °C (mm ² /s)	ASTN D7042	---
Kinematic Viscosity @ 100 °C (mm ² /s)	ASTN D7042	40-50
Density 15.6 °C (kg/m ³)	ASTM D4052	1020
Flash Point (°C)	ASTM D92	240
Pour Point (°C)	ASTM D97	Max 27
Aniline Point (°C)	ASTM D611	Max 40
VGC (Typical)	ASTM D2501	0.97
Oil Type	---	Aromatic